

# ROLEC Gehäuse-Systeme GmbH

## Lifoflex L 57312

Hardness test	58 ±0.3	Shore A
Density	0.90 ±2%	g/cm <sup>3</sup>
Tensile strength	3	MPa
Elongation at tear	> 550	%

- \*\* SBS rubber (styrol-butadiene-styrol-mass polymer)
- \*\* Adjusted so as to be physiologically safe
- \*\* Fulfils Toy Standard EN 71/3
- \*\* Sporadic contact with foodstuff is possible
- \*\* Free of halogens and heavy metals
- \*\* Supplementary UV stabilisation
- \*\* Odourless

- Processing: approx. 170°C – 190°C according to moulded part
- Impact pressure: approx. 10%
- Injection speed: fast

The mentioned values are average values, which may be modified through pigments or additives. For this reason, no guarantee can be granted for the mentioned material characteristics.

